

MARICO C4

SITE 2526 CB9

MAGOZASTAD 248 JP

Ornaments? Found on remains of HUT FLOOR

<sup>14</sup>C DATES FOR SITE:  $400 \pm 50$  BP,  $230 \pm 45$  BP,  $210 \pm 40$  BP  
+  $240 \pm 45$  BP.

DESCRIPTION: SEMI-CIRCULAR <sup>BRONZE</sup> ~~SPHER~~ BANGLE, BRIGHT GREEN IN COLOUR WITH GREY ADHERING MATRIX MATERIAL. ROUND CROSS-SECTION TAPERS TO A POINT AT ONE END, FRACTURED AT THE OTHER END.

MASS: 3,927 g

NON-MAGNETIC.

### Metallographic sample

- very clean, small inclusion stringers elongated parallel to length (2176, 2177)
  - inclusions (2178) 2-phase mixture of dark blue blobs in lighter blue matrix. Elongated, rounded, high aspect ratio - no red reflections.
- Some intergranular corrosion at outer margins.

Etched:  $FeCl_3$ : 2 seconds.

- Very angular, recrystallized grains with numerous annealing twins (2196)
- Some grain exhibit what look like acute exsolution features (2197-2199) - This is polishing damage.

Etched: ammonia:  $H_2O_2$

- Coring revealed under (IC) (2204-2205)
  - Recrystallized angular grains with annealing twins (2206)
- ~ASTM 8